














# WHITE CARMINE

**Tensiline®**  
OUTDOOR COMFORT

| Especificaciones técnicas<br>Technical specifications  | Norma<br>Standard  |  |
|--|--|--|
|  <b>Composición</b><br>Composition  | -  | 73% PVC + 27% PES  |
|  <b>Peso (g/m²)</b><br>Weight (g/m²)  | UNE EN 12127   | 518  |
|  <b>Espesor (mm)</b><br>Thickness (mm)  | UNE EN ISO 5084:1997   | 0.88   |
|  <b>Resistencia a la luz</b><br>(Escala de grises: 1-5)<br>Light Fastness (Grey scale: 1-5)   | EN ISO 105 B06:2002 (Interior)<br>EN ISO 105 B03:1994 (exterior)<br>EN ISO 105 B04:1998 (exterior)<br>EN ISO 4892-2 (exterior) | 5/5<br>4/5 White   |
|  <b>Resistencia a la luz</b><br>(Escala de azules: 1-5)<br>Light Fastness (Blue scale: 1-8) | EN ISO 105 B02:2002 (interior)   | 8/8<br>7/8 White   |
|  <b>Factor de Apertura (%)</b><br>Openness Factor (%)                                       | Internal method  | 22.5   |
|  <b>Resistencia a la rotura (daN/5 cm)</b><br>Breaking strength (daN/5 cm)                  | EN ISO 13934-1:1999  | Urdimbre / Warp: 241<br>Trama / Weft: 226  |
|  <b>Estiramiento (%)</b><br>Elongation at break (%)   | EN ISO 13934-1:1999  | Urdimbre / Warp: 20.3%<br>Trama / Weft: 19.9%  |
|  <b>Estiramiento 20 daN (%)</b><br>Elongation at 20 daN (%)                                 | EN ISO 13934-1:1999  | Urdimbre / Warp: 3.2%<br>Trama / Weft: 3.4%  |
|  <b>Resistencia al rasgado (daN)</b><br>Tearing resistance (daN)                            | DIN 53363:2003   | Urdimbre / Warp: 31.4<br>Trama / Weft: 31.2  |
| <b>Corrosión en ambiente salino</b><br>Corrosion in saline environment neutral fog   | EN ISO 112-017:92<br>ISO 9227:90   | Sin cambios en la superficie (máx. nivel)<br>Without changes in surface (max. level) |
|  <b>Clasificación de fuego</b><br>Fire classification                                       | EN 1021-1:2006<br>EN 1021-2:2006<br>IMO Resolution A652(16)  | Pass<br>Pass<br>Pass   |
|  <b>Ancho del rollo</b><br>Roll Width   | -  | 210 cm   |
|  <b>Longitud del rollo</b><br>Roll Length   | -  | 50 m   |

tensiline.com



0338/14



**PHthalate®**  
**FREE**



**Vertisol**

C. 17 km. 18,920 - 08403 Granollers [Barcelona]

Tensiline® is a brand of Vertisol Internacional, SRL, Barcelona, Spain.