














WHITE STEEL BLUE

TENSILINE®
OUTDOOR COMFORT

| Especificaciones técnicas Technical specifications | Norma Standard | |
|--|--|--|
|  Composición Composition | - | 73% PVC + 27% PES |
|  Peso (g/m²) Weight (g/m²) | UNE EN 12127 | 518 |
|  Espesor (mm) Thickness (mm) | UNE EN ISO 5084:1997 | 0.88 |
|  Resistencia a la luz (Escala de grises: 1-5) Light Fastness (Grey scale: 1-5) | EN ISO 105 B06:2002 (Interior) EN ISO 105 B03:1994 (exterior) EN ISO 105 B04:1998 (exterior) EN ISO 4892-2 (exterior) | 5/5 4/5 White |
|  Resistencia a la luz (Escala de azules: 1-5) Light Fastness (Blue scale: 1-8) | EN ISO 105 B02:2002 (interior) | 8/8 7/8 White |
|  Factor de Apertura (%) Openness Factor (%) | Internal method | 22.5 |
|  Resistencia a la rotura (daN/5 cm) Breaking strength (daN/5 cm) | EN ISO 13934-1:1999 | Urdimbre / Warp: 241 Trama / Weft: 226 |
|  Estiramiento (%) Elongation at break (%) | EN ISO 13934-1:1999 | Urdimbre / Warp: 20.3% Trama / Weft: 19.9% |
|  Estiramiento 20 daN (%) Elongation at 20 daN (%) | EN ISO 13934-1:1999 | Urdimbre / Warp: 3.2% Trama / Weft: 3.4% |
|  Resistencia al rasgado (daN) Tearing resistance (daN) | DIN 53363:2003 | Urdimbre / Warp: 31.4 Trama / Weft: 31.2 |
| Corrosión en ambiente salino Corrosion in saline environment neutral fog | EN ISO 112-017:92 ISO 9227:90 | Sin cambios en la superficie (máx. nivel) Without changes in surface (max. level) |
|  Clasificación de fuego Fire classification | EN 1021-1:2006 EN 1021-2:2006 IMO Resolution A652(16) | Pass Pass Pass |
|  Ancho del rollo Roll Width | - | 210 cm |
|  Longitud del rollo Roll Length | - | 50 m |

tensiline.com



0338/14



**PHthalate®
FREE**



Vertisol

C. 17 km. 18,920 - 08403 Granollers (Barcelona)

Tensiline® is a brand of Vertisol Internacional, SRL, Barcelona, Spain.